WELDER/WELDING OPERATOR PERFORMANCE QUALIFICATIONS (WPQ)

Welder's Na	ıme:	Adrian Hill	Clock No	v.: N	I/A	Stamp No.:	АН	
Welding Pro	ocess(es) Used:	GTA	W	Туре:	Manual	· -		
Identification	of WPS followed by Welder Du	ring Welding Test	F-GT-P8CVN					
Base Material(s) Welded: Stainless Steel					Thickness: 0.436"			
Manual of S	eniautomatic Variables for E	Each Process (QW-350)		Actua	l Values	Range Qua	alified	
Backing (metal, weld metal, welded from both sides, flux. Etc.) (QW-402)				N	None		either	
ASME P-N	o. (QW-403) 8	to ASME P-No. (QW	-403) 8	•	S.S	S.S.		
	Plate X	Pipe (enter diameter, if pipe)		2"	Dia.	1" and above		
Filler Metal Specification (SFA) 5.9 Classification (QW-404)					5.9		Same Group	
Filler Metal F-No.					6		Same Group	
Consumable insert for GTAW or PAW				N	N/A		N/A	
Weld Deposit Thickness for Each Welding Process				0.	0.499		0.063" - 0.872"	
Welding Position (1G, 5G, etc.) (QW-405)				•	6G		Unlimited	
Progression (uphill/downhill)				Uį	Uphill		Uphill	
Backing Gas for GTAW, PAW, or GMAW; Fuel Gas for OFW (QW-408)				Ar	Argon		Argon	
GMAW Transfer Mode (QW-409)					N/A		N/A	
GTAW Welding Current Type/Polarity				DC	DC/Str		DC/Str	
Machine Welding Variables for the Process Used (QW-360)				Actua	Actual Values		Range Qualified	
Direct/Remote Visual Control					N/A		N/A	
Automatic Voltage Control (GTAW)					N/A		N/A	
Automatic Joint Tracking					N/A		N/A	
Welding Position (1G, 5G, etc.)					N/A N			
Consumable Insert					I/A	N/A		
Backing (metal, weld metal, welded from both sides, flux, etc.)					I/A	N/A		
			Bend Test Results					
	Guided Bend Tests Type QW-462.2 (side) Results QW-462.3(a) (Tran			. R&F) Type				
	N/A	N/A	N/A		N	/A		
Vicual Evam	ination Results	Satisfactory						
	ic Test Results (QW-304)	Acceptable - Ma	nual Vanagas	MV	- W - 1			
	ernative qualification of groove		iluei vellegas	m vany			-	
•	Fracture Test	N/A	Length (in.) and Perce	ent of Defects		N/A		
Macro Test Fusion N/A		<u> </u>	N/A	2 0. 20.000	Concavity/Con			
Welding Cor		1 11100 200 3120	Adrian Hill of Andersor	n Welding	- Concavity/ C		14/74	
Mechanical Tests Conducted By		N/	N/A		Laboratory Test No. 22-0946 LT22-10-02		2-10-020	
Wicemanical	rests conducted by	14/7	1		ry restrict.	22 0340 2122	10 020	
We certify th	hat the statements in this recor	d are corrected and that the te	st coupons were prpared.	welded and teste	d in accordance	with the		
•	ts of Section IX of the ASME Cod		соврено него ргранов,					
		Organi			Anderson Welding			
Date:		October 14, 2022	Acc	Accepted By:				